



Test Report

Report No.: DGC170302027L

Page 1 of 3

Applicant : Sunfire Sports

Address : Yihongrong Industrial Park, Chiling, Houjie, Dongguan, Guangdong, China

The following sample(s) was/were submitted and identified on behalf of the client as:

Product Name : white woven fabric for blouse

Model : JF-XZF02

Brand : Sunfire

Manufacturer : Sunfire Sports

Address : /

Date of Sample Received : Mar. 02, 2017

Test period : Mar. 02, 2017 - Mar. 07, 2017

Test requested : As specified by client, to determine fuzzing and pilling performance test with the submitted sample.

Test method : Please refer to next page.

Test result : Please refer to next page.

Tested by:

Vien

Reviewed by:



Approved by:

Richard

Date:

Mar 07 2017

This document cannot be reproduced except in full, without prior written approval of NTEK. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

NTEK Testing Technology Co., Ltd.

Address: No.345, Baima Block, Guantai Road, Nancheng District, Dongguan, Guangdong, China

Tel: (+86-769) 23301666

Fax: (+86-769) 23301600

Email: service@ntek.org.cn

<http://www.dgntek.org.cn>



Test Report

Report No.: DGC170302027L

Page 2 of 3

Test Result:

Fuzzing and pilling performance (ISO 12945.1:2000)

Sample Description	White woven poly cotton fabric for shirts and blouse
Test condition	The rotational speed: 60r/min
	Test number: 7200r
Test Result:	4 Grade

Remark:

Visual assessment

Grade	Description
5	No change.
4	Slight surface fuzzing and/or partially formed pills.
3	Moderate surface fuzzing and/or moderate pilling. Pills of varying size and density partially covering the specimen surface.
2	Distinct surface fuzzing and/or distinct pilling. Pills of varying size and density covering a large proportion of the specimen surface.
1	Dense surface fuzzing and/or severe pilling. Pills of varying size and density covering the whole of the specimen surface.

This document cannot be reproduced except in full, without prior written approval of NTEK. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

NTEK Testing Technology Co., Ltd.

Address: No.345, Baima Block, Guantai Road, Nancheng District, Dongguan, Guangdong, China

Tel: (+86-769) 23301666

Fax: (+86-769) 23301600


Email: service@ntek.org.cn

<http://www.dgntek.org.cn>

Test Report

Report No.: DGC170302027L

Page 3 of 3

Photograph of Sample:

End of Report

This document cannot be reproduced except in full, without prior written approval of NTEK. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

NTEK Testing Technology Co., Ltd.

Address: No.345, Baima Block, Guantai Road, Nancheng District, Dongguan, Guangdong, China

Tel: (+86-769) 23301666

Fax: (+86-769) 23301600

Email: service@ntek.org.cn<http://www.dgntek.org.cn>